



Static Strength Characteristics of Mechanically Fastened Composite Joints

**(MSFC Center Director's Discretionary Fund Final Report,
Project No. 95-07)**

D.E. Fox and K.W. Swaim

Marshall Space Flight Center, Marshall Space Flight Center, Alabama

The NASA STI Program Office...in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the lead center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and mission, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results...even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:
NASA Access Help Desk
NASA Center for AeroSpace Information
7121 Standard Drive
Hanover, MD 21076-1320



Static Strength Characteristics of Mechanically Fastened Composite Joints

**(MSFC Center Director's Discretionary Fund Final Report,
Project No. 95–07)**

D.E. Fox and K.W. Swaim

Marshall Space Flight Center, Marshall Space Flight Center, Alabama

National Aeronautics and
Space Administration

Marshall Space Flight Center • MSFC, Alabama 35812

Available from:

NASA Center for AeroSpace Information
7121 Standard Drive
Hanover, MD 21076-1320
(301) 621-0390

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22161
(703) 487-4650

TABLE OF CONTENTS

1.	INTRODUCTION	1
2.	COUPON TEST CONFIGURATION	2
3.	TEST CONFIGURATION	3
4.	COUPON TEST RESULTS	4
5.	POSTTEST CORRELATION ANALYSIS	5
	5.1 Finite Element Modeling	5
	5.2 Bolted Joint Stress Field Mode FORTRAN Code	5
	5.3 Analytical Methods	5
6.	DISCUSSION	7
7.	CONCLUSION	8
	REFERENCES	21

LIST OF FIGURES

1. Coupon design	9
2. Phase A test data	9
3. Phase B test data	10
4. Phase C test data	10
5. Phase D test data	11
6. Phase E test data	11
7. Phase F test data	12
8. Phase G test data	12
9. Phase H test data	13
10. Phase I test data	13
11. Phase J test data	14
12. Phase K test data	14
13. Phase L test data	15
14. Phase M test data	15
15. Phase N test data	16
16. Phase O test data	16
17. Phase P test data	17
18. Phase Q test data	17
19. Phase R test data	18
20. Failure definition	18
21. Phase P coupon 4 test data	19
22. Phase P test coupon finite element model	19

LIST OF TABLES

1.	Test coupon design matrix	2
2.	Test coupon measured and predicted failure loads	6

TECHNICAL MEMORANDUM

STATIC STRENGTH CHARACTERISTICS OF MECHANICALLY FASTENED COMPOSITE JOINTS (MSFC Center Director's Discretionary Fund Final Report, Project No. 95-07)

1. INTRODUCTION

Composite materials used in spacecraft design offer many advantages in weight reduction, strength, and stiffness when compared to conventional materials. However, to utilize composites fully, a thorough understanding of the joint strength is required to prevent premature failure of a component at an interface. Analysis of bolted composite joints presents a great challenge to the structural analyst because of the large number of parameters, which will affect the strength. These parameters include edge distance, width, bolt diameter, laminate thickness, ply orientation, ply-stacking sequence, and bolt torque. Since the strength characteristic of a composite joint is unique due to the influence of these parameters, strength data derived from structural testing is required to allow for a thorough assessment.

The purpose of this research project is to evaluate the influence of various hole parameters on the structural strength characteristics of mechanically fastened composite joints. Testing is performed to determine the strength characteristics. Testing is followed by analysis and test data correlation. The successful correlation of test and analytical data will increase confidence in analysis methods, allow formulation of a coherent analysis methodology, and permit development of further analytical techniques. Also, the research will improve the understanding of testing composite joints and associated failure modes.

2. COUPON TEST CONFIGURATION

The composite coupons used for testing were fabricated from IM6/3501 graphite epoxy 32-ply quasi-isotropic laminate. This material system is selected because the extensive A-basis material data-base available. The quasi-isotropic laminate is selected because it is a typical design in structural applications. Eighteen different coupon configurations were designed with the following hole parameters:

Diameter: $d = 0.164, 0.194, 0.25$ in.
Edge Ratios: $e/d = 1.5, 2.0, 3.0$
Width Ratios: $w/d = 2.0, 2.5$
Torque: $Q = 0.0$ in.-lb

The general coupon design is shown in figure 1 and table 1.

Table 1. Test coupon design matrix.

Test Phase	d (in.)	e/d	e (in.)	w/d	w (in.)	No. of Coupons
A	0.164	1.50	0.246	2.50	0.410	7
B	0.164	2.00	0.328	2.50	0.410	7
C	0.164	3.00	0.492	2.50	0.410	7
D	0.164	1.50	0.246	4.00	0.656	7
E	0.164	2.00	0.328	4.00	0.656	7
F	0.164	3.00	0.492	4.00	0.656	7
G	0.190	1.50	0.285	2.50	0.475	7
H	0.190	2.00	0.380	2.50	0.475	7
I	0.190	3.00	0.570	2.50	0.475	7
J	0.190	1.50	0.285	4.00	0.760	7
K	0.190	2.00	0.380	4.00	0.760	7
L	0.190	3.00	0.570	4.00	0.760	7
M	0.250	1.50	0.375	2.50	0.625	7
N	0.250	2.00	0.500	2.50	0.625	7
O	0.250	3.00	0.750	2.50	0.625	7
P	0.250	1.50	0.375	4.00	1.000	7
Q	0.250	2.00	0.500	4.00	1.000	7
R	0.250	3.00	0.750	4.00	1.000	7

3. TEST CONFIGURATION

Coupon testing was performed using a double-lap shear test fixture. A shear pin was used to secure the coupon to the test fixture since torque from a fastener would add friction thus increasing the strength capability of the joint. A 5,000-lb tensile test machine was utilized to test the coupons. Testing followed the methodology specified in ASTM E 238-84, *Standard Test Method for Pin-Type Bearing Test of Metallic Materials*¹ and MIL-HDBK-17B, *Polymer Matrix Composites*.² All testing was performed using displacement or stroke control.¹

4. COUPON TEST RESULTS

Seven coupons were tested for each coupon configuration. The test data for each coupon test phase was plotted and reduced. Many of the plots exhibited a slight lag at the beginning of the load application, which represented the looseness or “slop” in the test setup. This “slop” was removed from the data and the coupon test data for each test phase was combined into a single plot. Numerical analysis was performed on the data utilizing the Chauvenet’s Criterion, thus eliminating dubious data points.³ Figures 2–19 show the coupon test data for each test configuration.

Based on the data reduction, an initial failure load was calculated. This failure load is defined to be the first hump in the curve, the point where the laminate could not sustain any more loading without significant displacement at the bolthole. The majority of the coupons tested in each test phase exhibited similar load and displacement characteristics up to the defined initial failure load. Ultimate failure is defined as the complete failure of the composite coupon. Not all test coupons were tested to ultimate failure, and components would never be designed to this ultimate failure load. Definitions for ultimate failure load, initial failure load, and first-ply failure are shown in figure 20.

5. POSTTEST CORRELATION ANALYSIS

Posttest analysis of the data was performed using finite element modeling techniques, FORTRAN programs, and closed-form methods. The finite element method and FORTRAN programs only looked at predictions of first-ply failure and did not consider any type of nonlinear effect or progressive failure. The closed-form method which is a modified equation to the bolthole bearing stress calculation was used in an attempt to match the initial failure load (previously defined) from the test data.

5.1 Finite Element Modeling

NASTRAN v70 finite element models, along with PATRAN, were used to perform analysis on the Phase P coupons. Models were built to gain understanding of the stress distributions on the various plies of the laminate. Loads were applied to the hole using cosine load distributions and the end of the coupon was fixed. Results of the analysis showed first-ply failure of the laminate to occur at loads >50 percent of the initial failure load. This was expected since the transverse strength of a single ply is significantly lower than the fiber direction. However, even after the predicted first-ply failure, the laminate still exhibited significant strength. Figure 21 presents the first-ply failure loads relative to initial failure load, and figure 22 shows the NASTRAN finite element model.

5.2 Bolted Joint Stress Field Model FORTRAN Code

The Bolted Joint Stress Field Model (BJSFM) FORTRAN code was also used to determine the stress distributions around the hole of the composite.⁴ It was found that the results from the BJSFM model were very similar to the NASTRAN model. The BJSFM calculates the bolthole load that corresponds to the first-ply failure of the laminate. For the Phase P coupon, the failure was calculated on the 90-degree ply in its transverse direction (reference fig. 21).

5.3 Analytical Methods

In an attempt to analytically predict the initial failure load as defined above, a modified bolthole bearing stress calculation was performed. The calculation is based on the bolthole diameter, the laminate thickness, and the calculated laminate strength at first-ply failure:

$$F_b = S * T * D \quad (1)$$

where:

- S = calculated laminate compression strength (psi)
(based on Tsai Hill Failure Theory)
- T = thickness (in.)
- D = hole diameter (in.)
- F_b = predicted failure load (lb).

Table 2 compares the test measured initial failure load and the predicted failure load using the above relationship.

Table 2. Test coupon measured and predicted failure loads.

Test Phase	Dia.(in.)	e/d Ratio	w/d Ration	Measured Failure (lb)	Predicted Failure (lb)
A	0.164	1.5	2.5	1277	1279
B	0.164	2.0	2.5	1318	1279
C	0.164	3.0	2.5	1139	1279
D	0.164	1.5	4.0	1388	1279
E	0.164	2.0	4.0	1302	1279
F	0.164	3.0	4.0	1256	1279
G	0.190	1.5	2.5	1454	1481
H	0.190	2.0	2.5	1438	1481
I	0.190	3.0	2.5	1410	1481
J	0.190	1.5	4.0	1424	1481
K	0.190	2.0	4.0	1395	1481
L	0.190	3.0	4.0	1371	1481
M	0.250	1.5	2.5	2203	1949
N	0.250	2.0	2.5	2191	1949
O	0.250	3.0	2.5	2055	1949
P	0.250	1.5	4.0	2157	1949
Q	0.250	2.0	4.0	2099	1949
R	0.250	3.0	4.0	1971	1949

6. DISCUSSION

As previously mentioned, the first-ply failure occurs at a load much lower than the initial failure load. All failures after first-ply failure are progressive-type failures where serious matrix damage, delamination, and fiber breakage is occurring and the stiffness is changing. Attempts were made during modeling to remove plies from the laminate after predicted failure to adjust stiffness and to determine new stress levels; however, no trend was found to match the test data. This method to model the progressive failure of the laminate was found inadequate.

As shown in table 2, the modified bolthole bearing stress calculation correlated well with the test data. This method is based only on a pin-type connection; however, a preloaded connection would only increase load-carrying capability.

7. CONCLUSION

The purpose of this research project was to evaluate the influence of various hole parameters on the structural strength characteristics of mechanically fastened composite joints. The purpose was not to develop failure theory codes that would be capable of evaluating different failure mechanisms in the composite-bolted connection for a given load.

The test data revealed that even after first-ply failure, the bolted connection (tested) still maintained considerable strength capability. The research performed for the configurations tested showed that if the BJSFM FORTRAN code or finite element models are used to predict bolthole failures based on ply properties, the actual bolthole capability is higher. The modified bolthole-bearing calculation agreed well with the initial failure load obtained from tests for the configurations tested.

The methods discussed here should not be substituted for testing of an actual configuration. This type of analysis offers a tool or methodology to the designer/analyst for preliminary design predictions to be made on the structural strength characteristics of mechanically fastened composite joints.




Figure 1. Coupon design.




Figure 2. Phase A test data.




Figure 3. Phase B test data.




Figure 4. Phase C test data.




Figure 5. Phase D test data.




Figure 6. Phase E test data.




Figure 7. Phase F test data.




Figure 8. Phase G test data.




Figure 9. Phase H test data.




Figure 10. Phase I test data.




Figure 11. Phase J test data.




Figure 12. Phase K test data.




Figure 13. Phase L test data.




Figure 14. Phase M test data.




Figure 15. Phase N test data.




Figure 16. Phase O test data.




Figure 17. Phase P test data.




Figure 18. Phase Q test data.




Figure 19. Phase R test data.




Figure 20. Failure Definition.




Figure 21. Phase P coupon 4 test data.




Figure 22. Phase P test coupon finite element model.

REFERENCES

1. ASTM E238-84, "Standard Test Methods for Pin-Type Bearing Test of Metallic Materials," ASTM.
2. MIL-HDBK-17B, "Polymer Matrix Composites," *Guidelines*, Vol. 1.
3. Holman, J.P.: *Experimental Methods for Engines*, 4th Ed., McGraw Hill Book Co., 1984.
4. AFWAL-TR-81-3041, "Effect of Variances and Manufacturing Tolerance on the Design Strength and Life of Mechanically Fastened Composite Joints," *Bolted Joint Stress Field Model (BJSFM) Computer Program User's Manual*, Vol. 3.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operation and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503				
1. AGENCY USE ONLY (Leave Blank)	2. REPORT DATE September 1999	3. REPORT TYPE AND DATES COVERED Technical Memorandum		
4. TITLE AND SUBTITLE Static Strength Characteristics of Mechanically Fastened Composite Joints (MSFC Center Director's Discretionary Fund Final Report, Project No. 95-07)		5. FUNDING NUMBERS		
6. AUTHORS D.E. Fox and K.W. Swaim				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) George C. Marshall Space Flight Center Marshall Space Flight Center, AL 35812		8. PERFORMING ORGANIZATION REPORT NUMBER M-947		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001		10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA/TM-1999-209735		
11. SUPPLEMENTARY NOTES Prepared by Structures, Mechanics, and Thermal Department, Engineering Directorate				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Subject Category 18 Nonstandard Distribution			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The analysis of mechanically fastened composite joints presents a great challenge to structural analysts because of the large number of parameters that influence strength. These parameters include edge distance, width, bolt diameter, laminate thickness, ply orientation, and bolt torque. The research presented in this report investigates the influence of some of these parameters through testing and analysis. A methodology is presented for estimating the strength of the bolt-hole based on classical lamination theory using the Tsai-Hill failure criteria and typical bolthole bearing analytical methods.				
14. SUBJECT TERMS composite, joint, bolt, testing			15. NUMBER OF PAGES 28	
			16. PRICE CODE A03	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT Unlimited	

National Aeronautics and

Space Administration

AD33

George C. Marshall Space Flight Center

Marshall Space Flight Center, Alabama

35812
